

A6
cont. crystalline resin, however, shapes of the ultra-high molecular weight polyethylenes are desirably flakes, powders, pellets or the like. / - -

IN THE CLAIMS:

Amend claims 1 and 3 as follows:

A7
1. (Amended) A liquid-crystalline resin composition comprising 0.01 to 10 parts by weight of an ultra-high molecular weight polyethylene having a molecular weight in excess of 600,000 and 100 parts by weight of a liquid-crystalline resin that exhibits anisotropic liquid-crystalline properties in a molten state.

A8
3. (Amended) The liquid-crystalline resin composition according to claim 1, wherein the liquid-crystalline resin is a liquid-crystalline resin which exhibits a flow temperature of 260 to 400 °C at a melt viscosity of 48,000 poise, when the melt resin is extruded from a nozzle at a heat-up rate of 4°C/minute under a load of 100kg/cm² using a capillary rheometer with a nozzle having an inside diameter of 1mm and a length of 10mm.
